Boost your Production





BT6600

Printing blanket for conventional inks and mixedmode applications

APPLICATION

Presses Substrates Inks Wash-up solvents Indentation plate/blanket presses <1080mm Indentation plate/blanket presses >1080mm Torque in N/m Sheet-fed Carton and paper Conventional and UV Conventional and UV 0.10mm-0.15mm (after running in) 0.15mm-0.20mm (after running in) Blanket across 20mm (-0/+10%)

CUSTOMER VALUE

Productivity:

- Reduction in press downtime for blanket change due to fatigue, double sheets/folded sheets and retain images in mixed-mode applications.
- Extended cleaning intervals, limited tendency for paper dust build up.

Quality:

- Balanced halftone and solid quality.
- Minimizes picking and stock delamination.
- Controlled dot sharpening on uncoated substrates.
- Attenuates streaks related to cylinder bounce and other sources of vibrations.

Sustainability:

- Contraction in printing blanket consumption due to fatigue and mechanical or chemical damage.
- Drop in wash and cleaning web usage as a result of extended cleaning intervals
- Cutback in start-up waste generated by extra blanket change and/or cleaning for paper dust build up during the print run.
- Enhanced operator health protection.
- Reinforced consumer protection.




Boost your Production



FEATURES

- Unique pressurized voids compressible layer technology.
- High chemical resistance to embossing/debossing in mixed-mode applications.
- Medium surface finish.
- Minimum gauge and energy loss over time.
- Compliant with REACH regulations.
- Isega-certified.



TECHNICAL DATA

Construction:

Fabric plies Compressible layer

Surface:

Surface material Colour Finish Roughness(Ra) Micro-hardness

Physical Properties:

Overall hardness Tensile strength Elongation at 500N/50mm Gauge loss at tensioning and running in Indentation at 100N/cm² Indentation at 200N/cm²

Gauge:

Nominal gauge Gauge uniformity per plate of max. 1SQM 3 Pressurized voids, closed cells

Mixed-mode rubber Green Ground & polished 0.9-1.2µm 63 Shore A

79 Shore A >3750N/50mm <2% <2% 0.14mm (7.1%) 0.23mm (11.7%)

1.96mm (+/-0.02mm) +/-0.015mm

